

Sales Specification

OXFILM 351

<i>Sales- Specifications</i>	Property		Limit	Unit	Test Method	PQR
	Appearance		Clear	Liquid	Visual Examination	
	Triethylenglycol-bis-2-ethyl-hexanoate	min.	97	% (a/a)	DIN 51405 (GC)	x
	Triethylenglycol-mono-2-ethyl-hexanoate (Mono Ester)	max.	1.5	% (a/a)	DIN 51405 (GC)	x
	Diethylenglycol-bis-2-ethyl-hexanoate	max.	0.5	% (a/a)	DIN 51405 (GC)	x
	Acid Value	max.	0.10	mg KOH/g	DIN EN ISO 2114 / ASTM D 1613	x
	Peroxide Value	max.	1.5	mäq. O/kg	RCH-AL079	x
	Ester Value		263 - 279	mg KOH/g	DIN EN ISO 3681	
	Hydroxyl Value	max.	5.0	mg KOH/g	DIN 53240	
	Water	max.	0.07	% (w/w)	DIN 51777 Part 1	x
	BHT Stabilizer	min.	50	mg/kg	DIN 51405 (GC), qual.	x
	Platinum/Cobalt Color (Hazen/APHA Color)	max.	30		DIN EN ISO 6271	x
	Density at 20 °C		0.962 - 0.972	g/cm ³	DIN 51757 Verf. D	
	Refractive Index n _D at 25 °C		1.441 - 1.447		DIN 51 423-2 / ASTM D 1747	

Product-No. 51005375

Date of Issue 2012-09-06

Version-No. 2

OXEA GmbH
Otto-Roelen-Straße 3
46147 Oberhausen
Germany

OXEA Corporation
1505 West LBJ Freeway
Suite 400
Dallas, TX 75234
USA

email: psq@oxea-chemicals.com

Page 1 of 1
11260A_SLS_EN_V2

The parameters marked with x are listed on the Product Quality Report (PQR).
Test methods used are available upon request. Contact your Sales Support for copies.

Typical properties are not part of the sales specification.

This information is based on our present state of knowledge and shall be intended to provide general notes on our products and their field of application. It shall therefore not be construed as guaranteeing specific characteristics of the products described and/or their suitability for a particular application. Any existing industrial property rights shall be observed. The quality of our products is warranted under our General Conditions of Sale.